

Amendments to the Claims

1. (Currently amended) A journal bearing system supporting a gear in a turbobfan transmission and comprising:
a bushing in the gear; and
a journal pin within the bushing and rotatable relative to the bushing about a longitudinal axis,
wherein at least one of the bushing and journal pin has an engagement surface with an engagement length comprising a base material and a solid lubricant, a concentration of the solid lubricant varying longitudinally along the engagement length.
2. (Original) The system of claim 1 wherein:
the concentration is higher near ends of the engagement length than in an intermediate portion.
3. (Original) The system of claim 1 wherein:
the concentration varies by at least 50% of a maximum value along said engagement length.
4. (Previously presented) The system of claim 1 wherein:
the base material comprises a coating applied to a substrate of said at least one of the bushing and journal pin.
5. (Previously presented) The system of claim 1 wherein:
the base material comprises a copper-based material; and
the solid lubricant comprises a metal.
6. (Original) The system of claim 5 wherein:
the solid lubricant metal comprises lead.
7. (Original) The system of claim 6 wherein the concentration is:
greater than 30% at first and second locations near first and second ends of the

engagement length; and

10-30% in an third location, between the first and second locations.

8. (Original) The system of claim 6 wherein the concentration is:
greater than 35% at first and second locations within first and second terminal 20% of the engagement length; and

10-30% over a majority of a central 50% of the length.

9. (Canceled)

10. (Currently amended) A hydrodynamic bearing apparatus comprising:
a bushing being a gear in a geared turbofan transmission;
a journal pin rotatable relative to the bushing about a longitudinal axis; and
means for providing extended operation after a lubricant loss comprising a coating on the bushing.

11. (Original) The apparatus of claim 10 wherein:
the means comprise a longitudinally-varying lead concentration within a copper matrix.

12. (Canceled)

13. (Canceled)

14. (Canceled)

15. (Previously presented) The system of claim 1 wherein the journal pin has at least one lubrication passageway.

16. (Previously presented) The system of claim 15 wherein the at least one lubrication passageway extends to the engagement surface.

17. (Previously presented) The system of claim 5 wherein the journal pin has at least one lubrication passageway.
18. (Previously presented) The system of claim 17 wherein the at least one lubrication passageway extends to the engagement surface.
19. (Previously presented) The system of claim 7 wherein the journal pin has at least one lubrication passageway.
20. (Previously presented) The system of claim 19 wherein the at least one lubrication passageway extends to the engagement surface.
21. (Previously presented) The apparatus of claim 10 wherein the journal pin has at least one lubrication passageway.
22. (Currently amended) The apparatus of claim 10 wherein:
the gear is steel; and
the means is on the bushing and the bushing is formed by a coating comprising comprises
substrate material and solid lubricant on an interior cylindrical surface of a steel the gear in a
geared turbofan transmission.
23. (Canceled)
24. (Previously presented) A hydrodynamic bearing apparatus comprising:
a bushing;
a journal pin rotatable relative to the bushing about a longitudinal axis;
at least one port in at least one of the bushing and journal pin for introducing a liquid lubricant; and
a solid lubricant within a matrix on at least one of the bushing and journal pin, a distribution of said solid lubricant forming means for providing extended operation after a loss of said liquid lubricant.

25. (Currently amended) The system of claim 9 1 wherein the transmission is liquid-lubricated and the solid lubricant concentration provides extended operation after a loss of liquid lubricant.
26. (Previously presented) The system of claim 4 wherein:
the base material comprises a copper-based material; and
the solid lubricant comprises a metal.
27. (Previously presented) The system of claim 1 wherein said concentration is a concentration of the solid lubricant within a matrix of the base material.
28. (New) A journal bearing system comprising:
a bushing; and
a journal pin within the bushing and rotatable relative to the bushing about a longitudinal axis,
wherein:
at least one of the bushing and journal pin has an engagement surface with an engagement length comprising a base material and a solid lubricant, a concentration of the solid lubricant varying longitudinally along the engagement length;
the base material comprises a copper-based material; and
the solid lubricant metal comprises lead;
the concentration is:
greater than 30% at first and second locations near first and second ends of the engagement length; and
10-30% in a third location, between the first and second locations.
29. (New) The system of claim 28 wherein the concentration is:
greater than 35% at said first and second locations, said first and second locations within first and second terminal 20% of the engagement length; and
10-30% over a majority of a central 50% of the length.